

Physical properties PETP TX

Properties	Test methods	Units	Values
Colour	-	-	light gray
Density	ISO 1183-1	g/cm ³	1.44
Water absorption:			
- after 24/96 h immersion in water of 23°C	ISO 62	mg	5 / 11
	ISO 62	%	0.06 / 0.13
- at saturation in air of 23°C / 50% RH	-	%	0.23
- at saturation in water of 23°C	-	%	0.47
Thermal Properties			
Melting temperature (DSC, 10°C/min.)	ISO 11357-1/-3	°C	245
Glass transition temperature	ISO 11357-1/-3	°C	-
Thermal conductivity at 23°C	-	W/(K.m)	0.29
Coefficient of linear thermal expansion:			
- average value between 23 and 60°C	-	m/(m.K)	65 x 10 ⁻⁶
- average value between 23 and 100°C	-	m/(m.K)	85 x 10 ⁻⁶
Temperature of deflection under load:			
- method A: 1.8 MPa	ISO 75-1/-2	°C	75
Max. allowable service temperature in air:			
- for short periods	-	°C	160
- continuously: for 5'000 / 20'000 h	-	°C	115 / 100
Min. service temperature	-	°C	-20
Flammability:			
- „Oxygen Index“	ISO 4589-1/-2	%	25
- according to UL 94 (3 / 6 mm thickness)	-	-	HB / HB
Mechanical Properties at 23°C			
Tension test:			
- tensile stress at yield / tensile stress at break	+ ISO 527-1/-2	MPa	76 / -
	++ ISO 527-1/-2	MPa	76 / -
- tensile strength	+ ISO 527-1/-2	MPa	76
- tensile strain at yield	+ ISO 527-1/-2	%	4
- tensile strain at break	+ ISO 527-1/-2	%	5
	++ ISO 527-1/-2	%	5
- tensile modulus of elasticity	+ ISO 527-1/-2	MPa	3300
	++ ISO 527-1/-2	MPa	3300
Compression test:			
- compressive stress at 1 / 2 / 5% nominal strain	ISO 604	MPa	24 / 47 / 95
Tensile creep:			
- voltage which leads to an elongation of 1,000 h to 1%	+ ISO 899-1	MPa	23
	++ ISO 899-1	MPa	23
Charpy impact strength - unnotched	+ ISO 179-1/1eU	kJ/m ²	30
Charpy impact strength - notched	+ ISO 179-1/1eA	kJ/m ²	2.5
Izod impact strength	+ ISO 180/A	kJ/m ²	2.5
	++ ISO 180/A	kJ/m ²	2.5
Ball indentation hardness	+ ISO 2039-1	N/mm ²	160
Rockwell hardness	+ ISO 2039-2	-	M94
Electrical Properties at 23°C			
Electrical strength	+ IEC 60243-1	kV/mm	21
	++ IEC 60243-1	kV/mm	21
Volume resistivity	+ IEC 60093	Ohm.cm	> 10 ¹⁴
	++ IEC 60093	Ohm.cm	> 10 ¹⁴
Surface resistivity	+ IEC 60093	Ohm	> 10 ¹³
	++ IEC 60093	Ohm	> 10 ¹³
Relative permittivity ϵ_r : - bei 100 Hz	+ IEC 60250	-	3.4
	++ IEC 60250	-	3.4
- bei 1 MHz	+ IEC 60250	-	3.2
	++ IEC 60250	-	3.2
Dielectric dissipation factor $\delta \tan$: - bei 100 Hz	+ IEC 60250	-	0.001
	++ IEC 60250	-	0.001
- bei 1 MHz	+ IEC 60250	-	0.014
	++ IEC 60250	-	0.014
Comparative tracking index (CTI)	+ IEC 60112	-	600
	++ IEC 60112	-	600

+ : Values for dry material
 ++ : Values for up to saturation in air of 23 °C / 50% RH material stored (mostly derived from large)

This table is a valuable help in the choice of a material. The data listed here fall within the normal range of products properties, but they should not be used to establish material specification limits nor used alone as the basis of design.

Note: 1 g/cm³ = 1000 kg/m³; 1 Mpa = 1 N/mm²; 1 kV/mm = 1 MV/m.