

# Physical properties PVDF

## Product characteristics:

- High purity
- Very good chemical resistance
- Excellent weather resistance

## Product applications:

- Chemical engineering and tank building
- Clean room and semi conductor industry
- Food processing industry

General properties	Test method	Unit	Value
Density	DIN EN ISO 1183-1	g/cm <sup>3</sup>	1.78
Water absorption	DIN EN ISO 62	%	0.0
Flammability (Thickness 3 mm / 6 mm)	UL 94		V0 / V0
<b>Mechanical properties</b>			
Yield stress	DIN EN ISO 527	MPa	55
Elongation at break	DIN EN ISO 527	%	30
Tensile modulus of elasticity	DIN EN ISO 527	MPa	2100
Notched impact strength	DIN EN ISO 179	kJ/m <sup>2</sup>	12
Shore hardness	DIN EN ISO 868	scala D	80
<b>Thermal properties</b>			
Crystalline grain melting range	ISO 11357-3	°C	178
Thermal conductivity	DIN 52612-1	W/(m*K)	0.2
Thermal capacity	DIN 52612	kJ/(kg*K)	1.20
Coefficient of linear thermal expansion	DIN 53752	10 <sup>-6</sup> /K	140
Service temperature, long term	Average	°C	-20 ... 140
Service temperature, short term (max.)	Average	°C	150
Heat deflection temperature	DIN EN ISO 75, Verf. A, HDT	°C	115
<b>Electrical properties</b>			
Dielectric constant	IEC 60250		9
Dielectric dissipation factor (50 Hz)	IEC 60250		0.02
Volume resistivity	IEC 60093	Ω*cm	10 <sup>14</sup>
Surface resistivity	IEC 60093	Ω	10 <sup>14</sup>
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV/mm	21

This table is a valuable help in the choice of a material. The data listed here fall within the normal range of products properties, but they should not be used to establish material specification limits nor used alone as the basis of design.